



## E502f.pl Technical Data Sheet



Firewin

2018-12

# Knauf Firewrap

## Product description

Knauf Firewrap consists of a graphite based reactive intumescent strip, which reacts to heat and closes the opening left by the softening plastic pipe or pipe insulation in a fire. The pipe wrap is installed completely around the pipes or insulation and secured with the self- adhesive tab.

### Storage

Unlimited storage time when stored in temperatures between 5°C and 30°C.

### Method of delivery

Knauf Firewrap 55mm, article no. 651077  
 Knauf Firewrap 82mm, article no. 651078  
 Knauf Firewrap 110mm, article no. 651079  
 Knauf Firewrap 125mm, article no. 651080  
 Knauf Firewrap 160mm, article no. 651084  
 Knauf Firewrap 200mm, article no. 651081  
 Knauf Firewrap 250mm, article no. 651082  
 Knauf Firewrap 315mm, article no. 651083  
 Knauf Firewrap Roll 50mmx25m, article no. 651085  
 Knauf Firewrap Roll 75mmx25m, article no. 651087  
 Knauf Firewrap Roll w/adh 50mmx25m, article no. 651088  
 Knauf Firewrap Roll w/adh 75mmx25m, article no. 651089

## Scope of application

Knauf Firewrap is designed to maintain the fire resistance of fire separating walls and floors when these are breached by plastic pipes, conduits or metal pipes with continuous combustible insulation, and may be used in drywalls, masonry or concrete walls and concrete floors.

It may be used both for plastic pipes (PVC, PP, PE ABS and Alupex), bundles of plastic pipes with or without cables as well as cable bundles. The Firewrap is cast into the wall or the floor by fixing it round the through-penetration with the attached sticker. It may also be fitted in Knauf FPC Panel.

## Properties

- For plastic pipe sizes from smallest pipes available to Ø400 mm with a wide range of pipe wall thicknesses
- For metal pipes with continuous combustible pipe insulation
- For plastic pipes with cables (conduits)
- Firewraps come in two different types; ready made for most common diameters and in 25 metre rolls for all diameters
- Fire classifications up to 240 minutes for both integrity and insulation
- ~~30 years~~ working life guarantee
- ~~ETA-18/0927~~
- ~~EAD-350141-00-1104~~

Technical Data	
Technical Approval	EAD 350454-00-1104
Durability according to EAD 350454-00-1104	Z <sub>2</sub> intended for use in internal conditions with humidity classes other than Z <sub>1</sub> , excluding temperatures below 0 °C.
Conditioning procedure	EN 13238:2010
Expansion ratio	28:1
Expansion pressure	55 N
Colour	Anthracite
Graphite weight	1.3 kg/m <sup>2</sup> per mm thickness
Graphite density	1300 kg/m <sup>3</sup>
Normal expansion time	Less than 10 minutes
Minimum expansion temperature	150 °C

## Pipe end configurations

When testing pipes, one can choose not to cap (or close) the pipe, or cap the pipe inside the furnace, or outside the furnace, or on both sides. The configuration chosen depends on the intended application of the pipe and/or the installation environment. The code defining if a pipe is capped is stated after the fire classification. For instance EI 60 C/U which means the pipe was capped inside the furnace, and uncapped outside the furnace. The test configuration defines the approvals possible.

Our suggestions for engineering judgments are:

Pipe end configurations:		
Intended use of pipe		Pipe end condition
Rainwater pipe	At roof	C/U <sup>1)</sup>
	Further below	C/C <sup>2)</sup>
Drainage or sewage pipe	At drainage	C/U <sup>1)</sup>
	Further below	C/C <sup>2)</sup>
Pipes in closed circuits (water, gas, vacuum systems, el. etc.)		C/C <sup>2)</sup>
Pipes with open ends and at least 50cm pipe on both sides		U/U

<sup>1)</sup> U/U condition can also be used  
<sup>2)</sup> U/C, C/U and U/U conditions can also be used

Sound insulation:	
Description	Sound reduction
Firewraps installed in FPC Panel	55 dB RW
Firewraps installed in FP Mortar	64 dB RW


The sound insulation value is only valid for the fire seal and not for other elements in the building construction.

The sound insulation has been tested by the accredited laboratory Exova BM Trada in Great Britain according to EN ISO 10140-2. Test report is available upon request.

Safety:
Please observe the EC Safety Data Sheet.

Sizes and Intended Use		
Size	Qty/Bag	Intended Use
Knauf Firewrap 55mm	25	Plastic pipes & conduits ≤ Ø55mm
Knauf Firewrap 82mm	25	Plastic pipes & conduits ≤ Ø82mm
Knauf Firewrap 110mm	25	Plastic pipes & conduits ≤ Ø110mm
Knauf Firewrap 125mm	20	Plastic pipes ≤ Ø125mm
Knauf Firewrap 160mm	12	Plastic pipes ≤ Ø160mm
Knauf Firewrap 200mm	1	Plastic pipes ≤ Ø200mm
Knauf Firewrap 250mm	1	Plastic pipes ≤ Ø250mm
Knauf Firewrap 315mm	1	Plastic pipes ≤ Ø315mm
Knauf Firewrap 50mmx25m	1	Metal pipes with combustible pipe insulation, plastic pipes & conduits
Knauf Firewrap 75mmx25m	1	

Knauf Sp. Z o.o.  
ul. Swaitowa 25  
02-229 Warsaw, ul.  
Poland

 (+48) 22 36 95 199

 [www.knauf.pl](http://www.knauf.pl)

 [info@knauf.pl](mailto:info@knauf.pl)

We reserve the right to make technical changes. The current version is always valid. Our warranty is expressly limited to our products in flawless condition. The stated constructional and structure properties, and characteristic building physics of Knauf systems can solely be ensured with exclusive use of Knauf system components or other products expressly recommended by Knauf. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas. All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission.

The stated constructional and structure properties, and characteristic building physics of Knauf systems can solely be ensured with exclusive use of Knauf system components or other products expressly recommended by Knauf.

NOTE: This document becomes invalid when replaced by a new version.